


## EcoBond®


### Recyclable Cleanroom Bond Paper



Berkshire is committed to lessen the environment impact of its manufacturing process and products through its **Green Scope Program**

EcoBond® is a latex free recyclable version of BCR® Cleanroom Bond. EcoBond® is made from the same pure and sustainable source of cellulose as our standard BCR®

Cleanroom Bond and is recommended for use in ISO Class 3-7 cleanrooms.



#### Key Attributes

- No latex binders
- Precision cut edges
- Lot traceability on each case
- Double packed for cleanliness
- Talc free
- High strength and heat resistance
- Good toner adhesion
- Medium weight, 85 g/m<sup>2</sup> (24lb) economical and durable for double-sided documents

#### Benefits

- Low in particles and fibers
- Low extractables and ions
- Compatible with toner and offset printing

#### Other Green Scope products:

- Lensx® 90
- Labx® 170
- Twillx® 1622

#### Environmental

- 100% recyclable
- Cellulose sourced from sustainable managed forests
- Meets RoHS guidelines

#### Applications

- Designed for use in ISO Class 3 and higher cleanroom environments
- Designed for the highest level of contamination control in critical processing applications
- Compatible with standard copiers and printers
- Steam autoclavable for aseptic applications
- Cleanroom manuals and work instructions
- Not recommended for use with inkjet printers

[www.berkshire.eu.com](http://www.berkshire.eu.com)

Contact: Tel 44 (0) 870 757 2877  
 enquiries@berkshire.uk.com

Americas	Tel 1 413 528 2602	Fax 1 413 528 2614	info@berkshire.com
Europe	Tel 44 (0) 870 757 2877	Fax 44 (0) 870 757 2878	enquiries@berkshire.uk.com
SE Asia	Tel 65 6252 4313	Fax 65 6252 4312	enquiries@berkshire.com.sg
Japan	Tel 81 3 5827 2380	Fax 81 3 5827 2382	master@berkshire.co.jp

## Technical Data

Attribute		Units	85g
<b>Basis Weight</b>		g/m <sup>2</sup>	84.9
<b>Caliper</b>		µm	98
<b>Fibers</b>		≥100µm/cm <sup>2</sup>	0.070
<b>Particles</b>			
	Wet Test	≥0.5µm	x10 <sup>3</sup> /cm <sup>2</sup> 0.47
<b>Tear</b>	MD	mN/4 sheets	851
	CD	mN/4 sheets	857
<b>Burst</b>		kPa	449
<b>Non-Volatile Residue</b>	DI Water	g/m <sup>2</sup>	0.20
	IPA	g/m <sup>2</sup>	0.050
<b>Ions</b>	Na <sup>+</sup>	ppm	150
	K <sup>+</sup>	ppm	4.0
	Ca <sup>++</sup>	ppm	1.4
	Mg <sup>++</sup>	ppm	0.20
	Cl <sup>-</sup>	ppm	75

### Notes:

- All values are statistical averages
- Due to differences in test methods applied and equipment utilized by different Bond manufacturers, valid product comparisons may only be obtained through side-by-side testing in the same test facility, under similar conditions
- Third party testing can be performed upon request

\* Please follow the link below for test methods  
<https://berkshire.uk.com/bond-test-methods/>

## Order Information

Product	Number	Size (cm)	Shts/pk	Pks/cs
EcoBond® 85g White	EC085A4WH	21 x 29.7	250	10
EcoBond® 85g Blue	EC085A4BL	21 x 29.7	250	10


## Other Berkshire products



**Wipers**




**Mop Systems**



**Face Masks**



**Glove Liners**



**Documentation Systems**



**Swabs**